

Application No.: 10/666,212

Case No.: 58807US002

Amendments to the Claims:

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (currently amended) Glass collectively comprising at least 85 ~~[[80]]~~ percent by weight of (i) at least one of Nb₂O₅ or Ta₂O₅, (ii) at least one of ZrO₂ or HfO₂, and (iii) at least one of Al₂O₃ or REO, and the glass containing not more than 15 ~~[[20]]~~ percent by weight collectively As₂O₃, B₂O₃, GeO₂, P₂O₅, SiO₂, TeO₂, and V₂O₅, with the proviso that the glass does not comprise 35.73 percent by weight Al₂O₃, 42.17 percent by weight La₂O₃, 17.1 percent by weight ZrO₂, and 5 percent by weight of one of Nb₂O₅ or Ta₂O₅, based on the total weight of the glass.

2. (original) The glass according to claim 1, wherein if Al₂O₃, REO, and at least one of ZrO₂ or HfO₂ are present, the glass comprises either not greater than 4 or at least 6 percent by weight of the at least one of Nb₂O₅ or Ta₂O₅, based on the total weight of the glass.

3. (original) The glass according to claim 1, wherein if Al₂O₃, REO, and at least one of ZrO₂ or HfO₂ are present, the glass comprises at least 6 percent by weight of the at least one of Nb₂O₅ or Ta₂O₅, based on the total weight of the glass.

4. (canceled)

5. (canceled)

6. (canceled)

7. (previously presented) The glass according to claim 3 collectively comprising at least 90 percent by weight of (i) at least one of Nb₂O₅ or Ta₂O₅, (ii) at least one of ZrO₂ or HfO₂, and (iii) at least one of Al₂O₃ or REO, based on the total weight of the glass.

Application No.: 10/666,212

Case No.: 58807US002

8. (previously presented) The glass according to claim 3 collectively comprising at least 99 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 , (ii) at least one of ZrO_2 or HfO_2 , and (iii) at least one of Al_2O_3 or REO, based on the total weight of the glass.

9. (currently amended) The glass according to claim 3 collectively having [[comprising]] 100 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 , (ii) at least one of ZrO_2 or HfO_2 , and (iii) at least one of Al_2O_3 or REO, based on the total weight of the glass.

10. (original) The glass according to claim 3 collectively comprising at least 70 percent by weight of Al_2O_3 , REO, and at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

11. (original) The glass according to claim 3, wherein the at least one of Nb_2O_5 or Ta_2O_5 is present in an amount of at least 10 percent by weight, based on the total weight of the glass.

12. (original) The glass according to claim 3 collectively comprising at least 70 percent by weight of REO, at least one of ZrO_2 or HfO_2 , and at least one of Nb_2O_5 or Ta_2O_5 .

13. (original) The glass according to claim 12, wherein the at least one of Nb_2O_5 or Ta_2O_5 is present in an amount greater than 5 percent by weight, based on the total weight of the glass.

14. (original) The glass according to claim 12, wherein the at least one of Nb_2O_5 or Ta_2O_5 is present in an amount of at least 10 percent by weight, based on the total weight of the glass.

15. (original) The glass according to claim 3 comprising greater than 5 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

Application No.: 10/666,212

Case No.: 58807US002

16. (original) The glass according to claim 3 comprising at least 10 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

17. (original) The glass according to claim 3 comprising at least 15 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

18. (original) The glass according to claim 3 comprising at least 20 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

19. (original) The glass according to claim 3 comprising at least 25 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

20. (original) The glass according to claim 3 comprising the at least one of Nb_2O_5 or Ta_2O_5 , in a range from 10 to 40 percent by weight, based on the total weight of the glass.

21. (original) The glass according to claim 3 collectively comprising at least 80 percent by weight of Al_2O_3 , REO, at least one of ZrO_2 or HfO_2 , and at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

22. (original) The glass according to claim 21, wherein the at least one of ZrO_2 or HfO_2 is present in an amount of at least 5 percent by weight, based on the total weight of the glass.

23. (original) The glass according to claim 21, wherein the at least one of ZrO_2 or HfO_2 is present in an amount of at least 10 percent by weight, based on the total weight of the glass.

24. (withdrawn) Ceramic comprising the glass according to claim 3.

Application No.: 10/666,212

Case No.: 58807US002

25. (withdrawn) A method for making the glass according to claim 3, the method comprising:

melting sources of (i) at least one of Nb_2O_5 or Ta_2O_5 , (ii) at least one of ZrO_2 or HfO_2 , and (iii) at least one of Al_2O_3 or REO, to provide a melt; and
cooling the melt to provide the glass.

26. (previously presented) A method for making ceramic comprising glass according to claim 3, the method comprising:

melting sources of (i) at least one of Nb_2O_5 or Ta_2O_5 , (ii) at least one of ZrO_2 or HfO_2 , and (iii) at least one of Al_2O_3 or REO, to provide a melt; and
cooling the melt to provide the ceramic.

27. (withdrawn) A method for making an article comprising glass, the method comprising:

providing glass powder comprising glass, the glass collectively comprising at least 70 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , and the glass containing not more than 30 percent by weight collectively As_2O_3 , B_2O_3 , GeO_2 , P_2O_5 , SiO_2 , TeO_2 , and V_2O_5 , with the proviso that the glass does not comprise 35.73 percent by weight Al_2O_3 , 42.17 percent by weight La_2O_3 , 17.1 percent by weight ZrO_2 , and 5 percent by weight of one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass, the glass having a T_g ; and

heating the glass powder above the T_g such that the glass beads coalesce to form a shape and provide the article comprising collectively comprising at least 70 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , and the glass containing not more than 30 percent by weight collectively As_2O_3 , B_2O_3 , GeO_2 , P_2O_5 , SiO_2 , TeO_2 , and V_2O_5 , with the proviso that the glass does not comprise 35.73 percent by weight Al_2O_3 , 42.17 percent by weight La_2O_3 , 17.1 percent by weight ZrO_2 , and 5 percent by weight of one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass of the article.

Application No.: 10/666,212

Case No.: 58807US002

28. (withdrawn) An optical waveguide comprising:
a substrate; and
a glass according to claim 3 on a surface of the substrate.

29. (withdrawn) The optical waveguide according to claim 28, wherein the glass is doped with a rare earth dopant.

30. (withdrawn) The optical waveguide according to claim 28 wherein the rare earth dopant is selected from the group consisting of cerium, praseodymium, neodymium, promethium, samarium, europium, gadolinium, terbium, dysprosium, holmium, erbium, thulium, ytterbium, or their other compounds and mixtures thereof.

31. (withdrawn) An optical waveguide comprising a glass fiber having a core material and a cladding surrounding the core material, wherein the core material comprises a glass according to claim 3.

32. (withdrawn) The optical waveguide according to claim 31, wherein the glass is doped with a rare earth dopant.

33. (withdrawn) The optical waveguide according to claim 29, wherein the rare earth dopant is selected from the group consisting of cerium, praseodymium, neodymium, promethium, samarium, europium, gadolinium, terbium, dysprosium, holmium, erbium, thulium, ytterbium, or their other compounds, and mixtures thereof.

34. (withdrawn) An optical amplifier comprising:
an optical pump source which provides optical pump light; and
an optical waveguide coupled to receive the optical pump light from the optical pump source, wherein the optical waveguide comprises a glass according to claim 3.

Application No.: 10/666,212

Case No.: 58807US002

35. (withdrawn) The optical amplifier according to claim 34, wherein the glass is doped with a rare earth dopant.

36. (withdrawn) The optical amplifier according to claim 35, wherein the rare earth dopant is selected from the group consisting of cerium, praseodymium, neodymium, promethium, samarium, europium, gadolinium, terbium, dysprosium, holmium, erbium, thulium, ytterbium, or their other compounds, and mixtures thereof.

37. (withdrawn) A method for amplifying optical signals, the method comprising: inputting the optical signals to an optical waveguide comprising a glass according to claim 3; and
applying pump light to the optical waveguide to cause the waveguide to provide optical gain to the optical input signals.

38. (withdrawn) The method according to claim 37, wherein the glass is doped with a rare earth dopant.

39. (withdrawn) Ceramic comprising at least 75 percent by volume glass, the glass collectively comprising at least 80 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 , (ii) at least one of ZrO_2 or HfO_2 , and (iii) at least one of Al_2O_3 or REO, and the glass containing not more than 20 percent by weight collectively As_2O_3 , B_2O_3 , GeO_2 , P_2O_5 , SiO_2 , TeO_2 , and V_2O_5 , with the proviso that the glass does not comprise 35.73 percent by weight Al_2O_3 , 42.17 percent by weight La_2O_3 , 17.1 percent by weight ZrO_2 , and 5 percent by weight of one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

40. (withdrawn) The ceramic according to claim 39, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass comprises either not greater than 4 or at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

Application No.: 10/666,212

Case No.: 58807US002

41. (withdrawn) The ceramic according to claim 39, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass comprises at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

42. (withdrawn) Glass-ceramic collectively comprising at least 70 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , and the glass-ceramic containing not more than 30 percent by weight collectively As_2O_3 , B_2O_3 , GeO_2 , P_2O_5 , SiO_2 , TeO_2 , and V_2O_5 .

43. (withdrawn) The glass-ceramic according to claim 42, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass-ceramic comprises either not greater than 4 or at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass-ceramic.

44. (withdrawn) The glass-ceramic according to claim 42, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass-ceramic comprises at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass-ceramic.

45. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 75 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

46. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 80 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

47. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 85 percent by weight (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

Application No.: 10/666,212

Case No.: 58807US002

48. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 90 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

49. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 95 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

50. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 99 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

51. (withdrawn) The glass-ceramic according to claim 42 collectively comprising 100 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , based on the total weight of the glass-ceramic.

52. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 70 percent by weight of Al_2O_3 , REO, and at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass-ceramic.

53. (withdrawn) The glass-ceramic according to claim 52, wherein the at least one of Nb_2O_5 or Ta_2O_5 is present in an amount of at least 10 percent by weight, based on the total weight of the glass-ceramic.

54. (withdrawn) The glass-ceramic according to claim 52 collectively comprising at least 70 percent by weight of REO, at least one of ZrO_2 or HfO_2 , and at least one of Nb_2O_5 or Ta_2O_5 .

Application No.: 10/666,212

Case No.: 58807US002

55. (withdrawn) The glass-ceramic according to claim 54, wherein the at least one of Nb_2O_5 or Ta_2O_5 is present in an amount greater than 5 percent by weight, based on the total weight of the glass-ceramic.

56. (withdrawn) The glass-ceramic according to claim 54, wherein the at least one of Nb_2O_5 or Ta_2O_5 is present in an amount of at least 10 percent by weight, based on the total weight of the glass-ceramic.

57. (withdrawn) The glass-ceramic according to claim 42 collectively comprising at least 70 percent by weight of Al_2O_3 , REO, at least one of ZrO_2 or HfO_2 , and at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass-ceramic.

58. (withdrawn) The glass-ceramic according to claim 57, wherein the at least one of ZrO_2 or HfO_2 is present in an amount of at least 5 percent by weight, based on the total weight of the glass-ceramic.

59. (withdrawn) The glass-ceramic according to claim 57, wherein the at least one of ZrO_2 or HfO_2 is present in an amount of at least 10 percent by weight, based on the total weight of the glass-ceramic.

60. (withdrawn) The glass-ceramic according to claim 42, with the proviso that the glass-ceramic does not comprise 35.73 percent by weight Al_2O_3 , 42.17 percent by weight La_2O_3 , 17.1 percent by weight ZrO_2 , and 5 percent by weight of one of Nb_2O_5 or Ta_2O_5 based on the total weight of the glass-ceramic.

61. (withdrawn) A method for making glass-ceramic according to claim 42, the method comprising:

heat-treating glass to convert at least a portion of the glass to crystalline ceramic and provide the glass-ceramic, the glass collectively comprising at least 70 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of

Application No.: 10/666,212

Case No.: 58807US002

ZrO₂ or HfO₂, and the glass-ceramic containing not more than 30 percent by weight collectively As₂O₃, B₂O₃, GeO₂, P₂O₅, SiO₂, TeO₂, and V₂O₅, based on the total weight of the glass.

62. (withdrawn) The method according to claim 61, with the proviso that the glass does not comprise 35.73 percent by weight Al₂O₃, 42.17 percent by weight La₂O₃, 17.1 percent by weight ZrO₂, and 5 percent by weight of one of Nb₂O₅ or Ta₂O₅ based on the total weight of the glass.

63. (withdrawn) A method for making glass-ceramic according to claim 42, the method comprising:

heat-treating ceramic comprising glass to convert at least a portion of the glass to crystalline ceramic to provide the glass-ceramic, the glass collectively comprising at least 70 percent by weight of (i) at least one of Nb₂O₅ or Ta₂O₅ and (ii) at least two of (a) Al₂O₃, (b) REO, or (c) at least one of ZrO₂ or HfO₂, and the glass-ceramic containing not more than 30 percent by weight collectively As₂O₃, B₂O₃, GeO₂, P₂O₅, SiO₂, TeO₂, and V₂O₅, based on the total weight of the glass.

64. (withdrawn) The method according to claim 63, with the proviso that the glass does not comprise 35.73 percent by weight Al₂O₃, 42.17 percent by weight La₂O₃, 17.1 percent by weight ZrO₂, and 5 percent by weight of one of Nb₂O₅ or Ta₂O₅ based on the total weight of the glass.

65. (withdrawn) A method for making a glass-ceramic article, the method comprising:

providing glass powder, the glass collectively comprising at least 70 percent by weight of (i) at least one of Nb₂O₅ or Ta₂O₅ and (ii) at least two of (a) Al₂O₃, (b) REO, or (c) at least one of ZrO₂ or HfO₂, and the glass containing not more than 30 percent by weight collectively As₂O₃, B₂O₃, GeO₂, P₂O₅, SiO₂, TeO₂, and V₂O₅, based on the total weight of the glass, the glass having a T_g; and

Application No.: 10/666,212

Case No.: 58807US002

heating the glass powder above the T_g such that the glass powder coalesces to form a shape and provide a glass article; and

heat-treating the glass article to convert at least a portion of the glass to crystalline ceramic to provide the glass-ceramic article.

66. (withdrawn) The method according to claim 65, with the proviso that the glass does not comprise 35.73 percent by weight Al_2O_3 , 42.17 percent by weight La_2O_3 , 17.1 percent by weight ZrO_2 , and 5 percent by weight of one of Nb_2O_5 or Ta_2O_5 based on the total weight of the glass.

67. (withdrawn) The method according to claim 66, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass comprises either not greater than 4 or at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

68. (withdrawn) The method according to claim 66, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass comprises at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

69. (previously presented) The glass according to claim 1 in the form of an IR window.

70. (withdrawn) The ceramic according to claim 39 in the form of an IR window.

71. (withdrawn) The glass-ceramic according to claim 42 in the form of an IR window.

72. (withdrawn) The method according to claim 27, wherein the glass of the glass powder comprises at least one of ZrO_2 or HfO_2 .

Application No.: 10/666,212

Case No.: 58807US002

73. (previously presented) Glass collectively comprising at least 97 percent by weight of (i) at least one of Nb_2O_5 or Ta_2O_5 and (ii) at least two of (a) Al_2O_3 , (b) REO, or (c) at least one of ZrO_2 or HfO_2 , and the glass containing not more than 3 percent by weight collectively As_2O_3 , B_2O_3 , GeO_2 , P_2O_5 , SiO_2 , TeO_2 , and V_2O_5 , with the proviso that the glass does not comprise 35.73 percent by weight Al_2O_3 , 42.17 percent by weight La_2O_3 , 17.1 percent by weight ZrO_2 , and 5 percent by weight of one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

74. (previously presented) The glass according to claim 73, wherein if Al_2O_3 , REO, and at least one of ZrO_2 or HfO_2 are present, the glass comprises either not greater than 4 or at least 6 percent by weight of the at least one of Nb_2O_5 or Ta_2O_5 , based on the total weight of the glass.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.